Attempting to reanodize titanium without completely stripping the existing oxide layer yields unpredictable additive colours.

My ultimate technique has yielded murky puddle water.