




25

40

**DO irradiate
polypropylene.**

**DO NOT irradiate
fluoropolymers.**

Radiation breaks
molecular backbones.

Chain scission
causes failure.

Gamma photons destroy polytetrafluoroethylene structures through severe polymer chain scission.
Never expose fluoropolymers to ionizing radiation sources.